

**COMPOSITION**

Modified resin

**IONIC STRUCTURE**

Cationic

**APPEARANCE**

Clear, colorless liquid

**PROPERTIES**

**MEGFIX F 50** improves washing and perspiration fastness of products dyed with direct dyestuffs.

Can be used with cationic and nonionic substances.  
Doesn't have a negative effect on the touch of the fabric.  
Doesn't have a negative effect on the light fastness.  
Is used by adding directly to the dyebath.

**APPLICATION**

In the exhaustion process  
40-50<sup>0</sup>a 1C, 20 min.

PH:4,5-5

After direct dyebath : % 1-5 (o.f.w.)

After reactive dyebath : % 0.1- 2

In foulard application

20-30<sup>0</sup>a 1C'de

PH:4,5-5

After direct dyebath :10- 30 g/l

After reactive dyebath : 1- 5 g/l

To remove MEGFIX F 50 from fabric surface,the below mentioned recipe can be used.

5 g/l hydrochloric acid, 60<sup>0</sup>a 1C, 30 minutes

**PACKING**

60 kg plastic drum and 200 kg barrel.