

## **MEGSOL DEM 111**

### **Dispersing and Levelling Agent**

<b>COMPOSITION</b>	Alkyl aryl polyglycol ether														
<b>IONIC STRUCTURE</b>	Nonionic														
<b>APPEARANCE</b>	Viscous liquid														
<b>PROPERTIES</b>	<p><b>MEGSOL DEM 111</b> provides uniform dyeing in polyester due to its good dispersing and levelling properties. Can be used in the same bath with anionic and cationic substances.</p> <p>Due to its ability to prevent the formation of oligomers, the color fastnesses of the products dyed with <b>MEGSOL DEM 111</b> are highly satisfactory.</p> <p>Is compatible with all types of carriers.</p> <p>Disperses unfixed dye particles in reductive washings and prevents their sedimentation.</p> <p>Is a good dispersing and levelling agent in wool / acrylic dyeing. In the dyeing process of acrylic fiber with cationic dyes, it prevents agglomeration of dyestuff and ensures proper maintenance of the dye tank and apparatus.</p> <p>Guarantees a high degree of rubbing fastness by ensuring suspension of the dye particles during oxidation.</p> <p>Can be used in finishing baths.</p> <p>Prevents sedimentation of bath ingredients in scouring baths.</p>														
<b>APPLICATION</b>	<table><tr><td>Polyester dyeing</td><td>: 1.0-2.0 %</td></tr><tr><td>Reductive washing</td><td>: 2.0-3.0 %</td></tr><tr><td>Indanthren dyeing</td><td>: 0.5-1.0 %</td></tr><tr><td>Acrylic dyeing</td><td>: 1.0 %</td></tr><tr><td>Wool dyeing</td><td>: 1.0-2.0 %</td></tr><tr><td>Wool-acrylic dyeing</td><td>: 1.0-3.0 %</td></tr><tr><td>Finishing and scouring baths</td><td>: 1.0 %</td></tr></table>	Polyester dyeing	: 1.0-2.0 %	Reductive washing	: 2.0-3.0 %	Indanthren dyeing	: 0.5-1.0 %	Acrylic dyeing	: 1.0 %	Wool dyeing	: 1.0-2.0 %	Wool-acrylic dyeing	: 1.0-3.0 %	Finishing and scouring baths	: 1.0 %
Polyester dyeing	: 1.0-2.0 %														
Reductive washing	: 2.0-3.0 %														
Indanthren dyeing	: 0.5-1.0 %														
Acrylic dyeing	: 1.0 %														
Wool dyeing	: 1.0-2.0 %														
Wool-acrylic dyeing	: 1.0-3.0 %														
Finishing and scouring baths	: 1.0 %														
<b>STORAGE</b>	Storage life, in its original container and at room temperature is 1 year.														
<b>PACKING</b>	60 kg plastic drum and 200 kg barrel.														