

### COMPOSITION

A stable and homogenous combination of polyglycol ethers and waxes.

### IONIC STRUCTURE

Nonionic

### APPEARANCE

Clear liquid

### PROPERTIES

**MEGSOL 109 VYM** provides evenness and slipperiness to the warp yarn. For this reason, can be used as afterwax. Prevents dusting and eliminates electric charges, therefore increases weaving productivity. Can be used to increase elasticity and to minimize hairiness of fibre in sizing baths. Is stable with water in all ratios. Can be easily washed out when necessary.

### APPLICATION

It should be diluted completely or partially depending on the production conditions and added to the waxing tank. The waxing should be 2-4 % of the warp weight. In sizing, the required quantity is approximately 3-4 % of starch.

### STORAGE

It should be protected from extreme cold. In its original container and at room temperature is 1 year.

### PACKING

60 kg plastic drum and 200 kg barrel.